

A PTFE thickened, medium viscosity, completely fluorinated grease intended for components where wide temperature and low torque are critical.

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-80 to 200	
Thickener		PTFE	
Base Oil	Type	Perfluoropolyether	
	Kinematic Viscosity	100°C 40°C	21.7 cSt 71 cSt
	Viscosity Index		330
	Flash Point	°C	300
	Pour Point	°C	-80
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		White	
Penetration (1/10 mm)	Unworked		297
	Worked	60 X	300
	NLGI Grade		1 - 2
Density	25°C		1.9 g/cm ³
Oil Separation	30 hour(s)	204°C	15.4
Evaporation	22 hour(s)	204°C	3.31 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product MSDS for detailed safety information because this product. (1407)